



XRD High-purity Fine Grain Isostatic Graphite

Technical Data Sheet

Forming: Isostatically Molded

Application: Photovoltaic, Vacuum Furnace, Precious Metal Smelting, EDM, General Purpose, etc.

Typical Properties at Room Temperature

Grade	Bulk Density	Electrical Resistivity	Hardness	Flexural Strength	Compressive Strength	Porosity	Ash Content	Ash Content (Purified)	Average Grain Size
	g/cm ³	μΩm	HSD	Mpa	Mpa	Vol. %	PPM	PPM	μm
xrd-1	1.83	11-14	50	45	100	12	800	50	12
xrd-6ks	1.86	10-13	65	48	100	11	1000	50	12
xrd-7k	1.83	11-14	67	50	110	12	1000	50	8
xrd-8k	1.86	10-14	72	55	120	12	1000	50	6
xrd-6w	1.90	8-9	53	55	95	11	/	50	12
xrd-7w	1.85	11-13	65	51	115	12	/	50	10
xrd-8w	1.91	11-13	70	60	135	11	/	50	10

Notes: This information is based on our present state of knowledge and is intended to provide general notes on our products and their uses. It should therefore not be construed as guaranteeing specific properties of the products described or their suitability for a particular application. The data listed falls within the normal range of product properties but should not be used to establish specification limits or used alone as the basis of design. XRD Graphite's liability to purchasers is expressly limited to the terms and conditions of sale.



Graphite Materials & Precision Machining | XRD GRAPHITE Manufacturing Ltd.

Sales & Customize: d.zhao@xrdgraphite.com

Application Support: info@xrdgraphite.com

www.graphitemachining.cn | www.xrdgraphite.com

For More Information

Please call us today or visit www.graphitemachining.cn and select Contact link to learn what XRD Graphite can do for you.

Telephone: 86.186.2536.8223

Address: High-tech Industrial Development Zone, Baofeng,

Pingdingshan City, Henan Province, China